Foam Stability Test									
							Temp Cement	87.7	
Date:	7-28-11						Water	82.5	
Technician:							RPM	12207	
Slurry Design:	109 gps 13% Foam (180 min) - Macond Cement Sample						1000 mL before foamed		
Theoretical Density of Slurry (ppg):	14.5ppg						Blender Cup Foamed		
Curing Temperature:							2057.86g ⇒ 1000.0mL STD. = 18.7		15.6ppg
Curing Time.									
Temperature of the Water:		Atm cond: 7-28-11 @ 2:46pm							
Specific Gravity of Water g/cm3:		CURESON: 07-28-11 @ 3:56 pm							
		Stability of Unset Foamed Cement Slurry							

Sample Number	Wt of Graduated Cylinder (g)	Slurry/Grad. Cylinder (g)	Volume of Sample (mL)	Density of Slurry (lb/gal)	S.G. (g/cm3)	S.G. (Top)	S.G. (Middle)	S.G. (Bottom)	
1	233.51	686.42	330.00	14.9	1.79				
2									
3									
4									
5									
6									
7									
8									

Comment: No Channeling noticed 6mL of void space (B) Bubble Breakout - minor.

Stability of Set Foamed Cement Slurry

Sample Number	Wt of Cube Section (g)	Wt of Volume of Removed Water (g)	Density of Top (lb/gal)	Wt of Cube Section (g)	Wt of Volume of Removed Water (g)	Density of Middle (lb/gal)	Wt of Sample Cube (g)	Wt of Volume of Removed Water (g)	Density of Bottom (lb/gal)
1									
2									
3									
4									
5									
6									
7									
8									

PROTECTED - SUBJECT TO PROTECTIVE ORDER

Exhibit No. 5940
Worldwide Court Reporters, Inc.

Foam Stability Test

	172811							TAP Cement	74.6	120mL oil → 600mL slurry
Date:								Water	74.1	
Technician:								RPM	12209	
Slurry Design:	10.9gps W/20% Base Oil (13% Foam) - 180mM							970 mL Base Oil before foamed		
Theoretical Density of Slurry (ppg)								Blender Chp Foamed		
Curing Temperature:								1569.35g → 980.0 mL	SG = 1.60	13.3 ppg
Curing Time:										
Temperature of the Water:										
Specific Gravity of Water g/cm3:		AM cond: 7-28-11 @ 11:50 a.m.								
		cubes on: 7-28-11 @ 3:20 p.m.								

Stability of Unset Foamed Cement Slurry

Sample Number	Wt of Graduated Cylinder (g)	Slurry/Grad. Cylinder (g)	Volume of Sample (mL)	Density of Slurry (lb/gal)	S.G. (g/cm3)	S.G. (Top)	S.G. (Middle)	S.G. (Bottom)	
1	238.56	621.41	250.00	12.174	1.33				
2									
3									
4									
5									
6									
7									
8									

Comment: Minor Bubble Breakout

Stability of Set Foamed Cement Slurry

Sample Number	Wt of Cube Section (g)	Wt of Volume of Removed Water (g)	Density of Top (lb/gal)	Wt of Cube Section (g)	Wt of Volume of Removed Water (g)	Density of Middle (lb/gal)	Wt of Sample Cube (g)	Wt of Volume of Removed Water (g)	Density of Bottom (lb/gal)
1 Top	49.15	33.52	12.21						
2 Mid	44.84	43.38				12.85			
3 Bottom	32.51	45.92							13.15
4 Cube	230.19	148.38	12.89						
5									
6									
7									
8									

PROTECTED - SUBJECT TO PROTECTIVE ORDER

DJIT003-000127