

SUBJECT: SA-541 Delayed Hydrating Suspending Aid

Table 1—SA-541 Physical Properties			
Function	suspending aid and free-water control agent	Part Number	516.01068
Color	cream to pale color	Specific Gravity	1.40
Form	powder	Bulk Density	47 lb/ft ³

Description


SA-541 (Part No. 516.01068) is a suspending aid and free-water control agent that has minimal effect on surface mixing viscosity. It can be used when other suspending aids, such as FWCA or FDP-C533 cause slurry mixing problems. When cement slurries containing SA-541 are heated to temperatures greater than 150°F, the material yields to suspend downhole solids.

SA-541 counteracts thermal thinning of cement slurries while allowing them to be easily mixed. SA-541 is mildly retarding and can be used at temperatures as low as 150°F. The amount of SA-541 used in a cement slurry depends on several factors, some of which are listed below:

- water-to-cement ratio
- addition level of dispersing additives such as retarders
- presence of KCl
- amount of weighting material contained in heavyweight slurries

Normally, the addition level of SA-541 will not exceed 0.5% by weight of cement (BWOC).

SA-541 will not work in saturated salt slurries.



NOTICE: This document is confidential, proprietary property of Halliburton Energy Services. It is supplied for use by Halliburton Energy Services employees only and shall not be copied, published or disclosed in whole or in part without the prior written consent of Halliburton Energy Services.

Table 2—Effect of Temperature on SA-541 Hydration (Premium Cement, 35% SSA-2™ silica, 0.5% Halad®-413 additive, 0.5% SCR-100™ retarder, 4.3 gal/sk water, 17.3 lb/gal)			
SA-541 (% BWOC)	Temperature (°F)	Fann Data (600-300-200-100)	Yield Point (lb/100 ft²)
0.0	Ambient ^a	250-124-82-40	—
0.0	190	122-54-36-16	—
0.1	Ambient ^a	284-144-100-50	4
0.1	85 ^b	270-138-92-44	6
0.1	110	212-102-72-38	—
0.1	140	170-80-50-25	—
0.1	160	264-136-92-44	8
0.1	190	344-194-136-80	44
0.2	190	480-300-226-140	120

^aFann readings taken immediately after mixing.

^bStirred for 1 hour on atmospheric consistometer before Fann readings were taken.

Table 3—Thickening Times of Slurries Containing SA-541 (Premium Cement, 4.3 gal/sk water 16.4 lb/gal)		
SA-541 (% BWOC)	Test Temperature (°F)	Thickening Time (hr:min)
0.0	125	2:23
0.5	125	2:39
Premium Cement, 35% SSA-2™ silica, 0.5% SCR-100™ retarder, 0.5% Halad®-413 additive, 4.3 gal/sk water, 17.3 lb/gal		
0.0	200	4:25
0.1	200	3:50

Table 4—UCA Data for Slurries Containing SA-541 (Premium Cement, 4.3 gal/sk water, 16.4 lb/gal at 150°F)			
SA-541 (% BWOC)	Initial Set (hr:min)	500 psi (hr:min)	24-hr strength (psi)
0.0	2:30	4:12	3,080
0.5	9:01	12:55	1,680
Premium Cement, 35% SSA-2™ silica, 0.5% Halad®-413 additive, 0.5% SCR-100™ retarder, 4.3 gal/sk water, 17.3 lb/gal at 200°F			
0.0	11:16	—	4,710
0.1	13:00	—	4,200

Table 5—Suspension Properties of SA-541 in Heavyweight Slurries
(Premium Cement, 35% SSA-2™ silica, 22 lb/sk Hi-Dense® No. 4 weight additive, 0.6% Halad®-413 additive, 1.2% SCR-100™ retarder, 0.6% HR®-25 additive, 4.46 gal/sk water, 18.5 lb/gal)

SA-541 (% BWOC)	Temperature (°F)	Fann Data (600-300-200-100)	Yield Point (lb/100 ft ²)
0.0	Ambient ^a	526-270-180-90	14
0.0	190	192-80-52-24	—
0.1	Ambient ^a	558-300-190-92	42
0.1	190	500-280-192-100	60
0.1	300 ^b	600+400-260-130	—

^aFann readings taken immediately after mixing.

^bHeated to 300°F in stirring fluid-loss cell, then cooled to 150°F before Fann readings were taken.

Table 6—Effect of Temperature on Hydration of SA-541
(Premium Cement, 35% SSA-2™ silica, 1% HR®-15 additive, 4.3 gal/sk water, 17.3 lb/gal)

SA-541 (% BWOC)	Temperature (°F)	Fann Data (600-300-200-100)	Yield Point (lb/100 ft ²)
0.0	Ambient ^a	164-78-50-26	—
0.0	140	86-30-20-10	—
0.2	Ambient ^a	184-84-56-28	—
0.2	140	312-170-118-64	28
0.2	180	348-238-188-128	128
0.5	Ambient ^a	230-110-70-36	—
0.5	140	494-328-260-176	162
0.5	180	600+ -600+ -600+ -542	—

^aFann readings taken immediately after mixing.

Table 7—High-Temperature Suspension Properties of SA-541
(Premium Cement, 35% SSA-1™ flour, 1.0% Halad®-413 additive, 1.0% SCR-100™ retarder, 0.5% HR®-25 additive, 4.3 gal/sk water, 17.3 lb/gal)

SA-541 (% BWOC)	Temperature (°F)	Fann Data (600-300-200-100)	Yield Point (lb/100 ft ²)
0.0	190	186-86-56-28	—
0.1	190	562-304-204-104	46
0.1	300 ^a	570-296-190-92	22

^aHeated to 300°F in stirring fluid loss cell, then cooled to 150°F before Fann readings were taken.

Table 8—SA-541 in KCl Containing Cement
(Premium Cement, 35% SSA-2™ silica, 0.8% Halad®-413 additive,
0.2% SCR-100™ retarder, 6.2 gal/sk water, 16.1 lb/gal)

SA-541 (% BWOC)	KCl (% BWOW)	Temperature (°F)	Fann Data (600-300-200-100)	Yield Point (lb/ft ²)
0.0	0	Ambient ^a	76-38-24-12	0
0.0	0	190	200-108-77-44	16
0.1	3	190	100-46-30-16	— ^b
0.2	3	Ambient ^a	68-32-20-12	—
0.2	3	190	130-65-45-25	0

^aFann readings taken immediately after mixing.

^bSlurry had 1mL of free water and no settling.